


Pergasol™ Direct Dyes (Powder)

Pergasol

(0,5% dye)



Solenis Trade Name	PERGASOL YELLOW 5R-E	PERGASOL RED 2G-E	PERGASOL RED 2BE	PERGASOL RED 4B	PERGASOL RED 7BE	PERGASOL BLUE GL 250%	PERGASOL TURQUOISE RE	PERGASOL BLACK GN-E
L*	77.4	54.9	52.7	66.6	63.4	46.9	65.4	46.3
a*	18.8	51.8	44.4	39.5	38.6	4.1	-25.4	-4.3
b*	54.5	21.9	6.2	5.7	-7.4	-21.8	-29.6	-3.4
Lightfastness	2-3	2	2-3	2	2	4	5-6	1-2
Backwater	3-4	4	2	2	4	4	1	1
Solubility g/l (30°C)	<=40	<=60	<=60	<=70	<=60	<=50	<=25	<=45



Solenis Trade Name	PERGASOL BLACK 0B	PERGASOL BLACK 0C
L*	48.2	43.9
a*	-1.5	-1.6
b*	-8.4	-8.6
Lightfastness	1	2-3
Backwater	4	3-4
Solubility g/l (30°C)	<=15	<=90

Application Conditions:

70% bleached Pine / 30% bleached Beech
30°SR

0,3% Pergafix™ AP9397 fixative

Furnish

L* 95,1
a* -0,1
b* 3,8